

Name	SPECCHIO RIFLESSI NATURALI SPECCHIO
Description	Self-glossing, decorative Venetian Stucco
Main Features	Self-glossing Stucco for interior surfaces.
Baldini Tecnicolor	More than 1000 colours for Stucco Specchio Autolucidante using the Baldini Tecnicolor Edilizia Tintometric System
Classification (UNI 8681)	E. 2/4.C.O.A.2.FA Water soluble, single-component, physically drying, opaque, acrylic Stucco for base coats and finishes.
Application Cycle	<p>New plaster that is firm and even does not need any preparation. Old surfaces that are not very consistent or very absorbent must be brushed down and bonded using a transparent Solvent-based Fixative. Timber surfaces must be treated with one or more coats of Solden Plus until a perfectly smooth surface is obtained.</p> <p>A first coat of Stucco Veneziano is applied to the surfaces using a stainless steel plastering trowel. Wait at least 8-24 hours and then sand down carefully using fine sandpaper. If necessary repeat these first two steps. Alternatively, Stuccotone paste or powder can be applied to plaster surfaces.</p> <p>Then spread the Stucco Specchio Autolucidante using a stainless steel plastering trowel, in ever decreasing thicknesses. When the material starts to dry, finish the surface with a stainless steel plastering trowel to produce the required sheen.</p>
Practical Advice	<p>Do not apply to surfaces exposed to direct sunlight or strong winds. When working with very absorbent interior surfaces, first apply one coat of water-based Fixative.</p> <p>On finishing work, immediately wash the tools with water.</p> <p>For perfect uniformity in colour, mix using a paddle, then shake in a mixer for at least 10 minutes.</p> <p>Ambient and surface conditions: Ambient Temperature : min. 5°C / max 35°C; Ambient Relative Humidity : < 80%; Surface Temperature : min 5°C / max 35°C; Surface Dampness : < 10% R.H.</p>
Safety data	<ul style="list-style-type: none">• Keep the tin tightly closed, upside down and protected from frost.• No labelling required.• User information is contained in the relevant safety sheet.• Empty containers and containers with traces of dried product film must be disposed of according to local regulations.
Tender item	Application of RIFLESSI NATURALI SPECCHIO with an average consumption of _____ l per sq. m, to be applied in two coats at a cost of € _____ per sq. m, including materials and labour and excluding scaffoldings and surface dressing.

Specifications and other technical information	Method	Main Data at 20°C and 60% Relative Humidity
Coat finish and aspect		-
Density g/ml	BVL 007 (UNI 8910)	1.810 ÷ 1.900
Brookfield viscosity cps		Paste
Calculated spreading rate For 40 m thickness	BVL 059	2 ÷ 3 sqm / kg 3,5 ÷ 5,6 sqm / lt
Recommended dry film thickness microns per coat	BVL 066	40
Flash point °C	BVL 046 (UNI 8909)	Not flammable
Shelf life (in cool and dry place)	BVL 064 (UNI 10154)	At least 36 months
Solid content Weight %		80 - 85
Hard dry hrs	BVL 066	8
Dry to recoat hrs	BVL 048	24
Exteriors / Interiors		No / Yes
Colours		According to shade card
Binder		Acrylic
Thinner		Water
Tool cleaner		Water
Trowel application		Ready to use

This information is based on our best technical and practical knowledge. However, since the actual conditions in which the products are used beyond our direct control, we provide no guarantee as to effectiveness of the advice and suggestions contained herein. If in doubt, it is advisable to conduct preliminary tests and/or call our technical service.

Atova International

2452 N. Harlem Ave.
Elmwood Park, IL 60707
Phone: 1-866-452-9982
Fax: 1-708-452-8331
www.paintandplasters.com
techsupport@paintandplasters.com

